Item Code: 95051K Feb 2013 v2



Provides maintenance free PRODUCTION - LONGER

STEEL LIQUID TECHNICAL REFERENCE INFORMATION



STEEL LIQUID is a pourable steel epoxy liquid that can be used in casting, filling and levelling applications. It cures to a tough inert material that may be machined, drilled or tapped later if required. The innovative technology used in the development of this product results in a finish that can also be easily applied to equipment to maximize service by providing protection against corrosion and chemical attack.

TYPICALLY USED ON:

Bedding Casting repairs

Chocking General adhesive duties

Holding fixtures Levelling
Moulding Reproductions

Void filling

GENERAL PRODUCT INFORMATION

USERS DATA	
Ratio by weight	10:1
Ratio by volume	6:1
Pot Life 500g minutes @ 24°C	20
Mixed colour	Grey
Mixed consistency @ 24°C	Thick Liquid
Specific gravity when mixed	1.55
Coverage, kg/m² @ 1 mm	1.6
TYPICAL CURED PROPERTIES	
Compressive strength ASTM D695, Mpa	68
Tensile strength ASTM D638, Mpa	30
Flexural strength ASTM D790, Mpa	22
Hardness, Shore D	80
Thermal conductivity ATSM C177, Kcal/m.hr° C	0.42
Coefficient of thermal expansion ASTM C531	4.6
(cm/cm/°C) x 10-5	
Dielectric constant ASTM D150 (150KHz)	4.2
Maximum operating temperature, °C	115
Heat deflection temperature ASTM D648, °C	75
Cure to handling @ 5mm, Minutes	120
Cure time @ 5mm, Hours	24

CHEMICAL RESISTANCE

Tested at 21°C. Samples cured for 10 days at 25°C. Curing at elevated temperatures (ie: > 45°C) will improve chemical resistance.

- 1 = Continuous or long term immersion
- 2 = Short term immersion
- 3 = Splash and spills
- 4 = Avoid contact

Acetic Acid, 10 %	2	Acetone	2
Acetic Acid, Glacial	2	Ammonium Chloride	1
Hydrochloric Acid, 5 %	2	Beer	1
Hydrochloric Acid, 10 %	2	Dichloromethane	4
Hydrochloric Acid, conc	3	Diesel Fuel	1
Nitric Acid, 5 %	2	Isopropyl Alcohol	1
Nitric Acid, 10 %	3	Kerosene	1
Phosphoric Acid, 5 %	2	Petrol	1
Phosphoric Acid, 20 %	3	Salt Water	1
Sulfuric Acid, 5 %	2	Sewage	1
Sulfuric Acid, 20 %	3	Skydrol	1
Ammonium Hydroxide, 5 %	1	Sodium Cyanide	1
Ammonium Hydroxide, 20 %	1	Sodium Hypochlorite	1
Potassium Hydroxide, 5 %	1	Toluene	2
Potassium Hydroxide, 20 %	1	Trichloroethane	2
Sodium Hydroxide, 5 %	1	Wine	1
Sodium Hydroxide, 20 %	1	Xylene	1

This information is supplied as an indicative reference only. Caution should be used where direct comparisons are to be made.

SURFACE PREPARATION

It is essential that all surfaces to be treated are properly prepared to obtain a strong bond between the substrate and the product.

- All oil, dirt and other loose contamination must be removed by washing. degreasing or blasting.
- Surfaces should preferably be abrasive blasted although roughening using mechanical alternatives such as wire brush or abrasive disc can be used to leave a clean surface, free of scale, rust and other foreign substances

For maximum adhesion to metallic surfaces, grit blast to expose a sound substrate with a nominal surface profile of 50-80 micron. Application should take place immediately after preparation to avoid oxidation of the freshly prepared surface.

Surfaces that have been exposed to extreme environments such as continuous operation in sea water or petroleum products may necessitate alternate preparation procedures. Consult National or International standards where possible.

APPLICATION

Apply a very thin scratch or smear coat directly to the prepared surface to maximize surface contact before proceeding to apply additional product to the desired build. Ensure product has been worked into all cracks and voids to eliminate air bubbles. If applying several coats or layers, any previously applied product must be roughened if it has been left to cure for more than 24

CLEAN UP

Clean tools and equipment immediately after use with Cleanup or a heavy duty industrial hand cleaner or detergent.

Variations in cure may arise due to the amount of material being applied, the thickness of material being applied, the surface temperature, and the product temperature. The cure may be increased by applying external heat to the prepared surface before application of the product. This can be done with heat lamps or other heat sources. The cure may be decreased by cooling the product

SHELF LIFE

Store away from heat and direct sunlight. A minimum of 2 years should be expected if held in original unopened containers.

WARRANTY

Since the storage, handling and use of this product is beyond our control, this product is supplied without guarantee. Furthermore, nothing should be construed as a recommendation to use this product in conflict with existing patents

Material Safety Data (PART A)

U.N. Number None Allocated Dangerous Goods Class and Subsidiary Risk: Hazchem Code: Poisons Schedule: None Allocated None Allocated

Physical Description / Properties

Grey Slight 0% Colour: Odour Percent Volatiles: Specific Gravity: Solubility in Water: .65 Non Soluble Flash Point (°C): Flammability Limits: Non Flammable Not Applicable

Ingredient Chemical entity

Epoxy Resin Metallic Fillers (eg: Steel, Aluminium, etc) Natural Fillers (eg: Talc, Titanium Dioxide) Thixotropes & Suspending Agents (eg: Cellulose) Medium Medium Medium

(High>60%) (Medium 10% - 60%) (Low<10%)

Proportion

Material Safety Data (PART B)

U.N. Number Dangerous Goods Class None Allocated and Subsidiary Risk: Hazchem Code: None Allocated None Allocated

Physical Description / Properties

Clear Yellow Slight Amine 0% Colour: Odour: Percent Volatiles: Specific Gravity: Solubility in Water: Flash Point (° C): Flammability Limits: 1.0 Non Soluble Non Flammable Not Applicable

Ingredient Chemical entity Polyamide/Aliphatic Amine Prepolymer Proportion High

HEALTH HAZARD INFORMATION

Health Effects

Swallowed: Possible irritant. Can result in nausea, vomiting, stomach

pain or discomfort.
Irritation, no corneal damage likely.
Possible irritant. Prolonged or repeated uncontrolled exposure may lead to dermatitic effects. Inhaled:

None likely, unless heated to extremely high temperatures, in which case irritation of the respiratory tract may occur.

First Aid

Swallowed DO NOT induce vomiting. Give a glass of water and contact a doctor or the Poisons Information Centre. Eye: Hold eye lids open and flood with water for 15 minutes

See a doctor.

Remove contaminated clothing, wash affected area with soap and water. If swelling or blisters occur, seek Skin:

Not considered likely, however, if effects are perceived, remove to fresh air and rinse mouth and nasal passage with water. Inhaled

PRECAUTIONS FOR USE

Not determined for this product. Exposure limits

Not determined to runs produce. Conventional airflow is generally acceptable. In confined areas, exhaust fans should be utilised in accordance with proper safe handling procedures.

Avoid contact with skin and eyes. Wear coveralls, rubber gloves and eye protection while handling.

Non flammable.

Personal protection

Flammability

Item Code: 95051K Feb 2013 v2

SAFF	HANDI	ING	INFORM	MATION	d

(High>60%)

Storage:

(Medium 10% - 60%) (Low<10%)

Spills and Disposals: Fire/Explosion Hazard:

No special transporting requirements. When storing, do not allow to freeze and store below 35°C. i.e. Store between 5°C and 35°C.
Pick up and consult local authorities for disposal.
Alternatively, cure as per directions for use and landfill.
This product is non flammable, it may burn although auto ignition is highly unlikely. Fumes in the form of oxides of carbon and nitrogen will be evolved during combustion. Self contained breathing apparatus should be available for firemen and water sprays, foam, dry chemical or CO2 should be used.

should be used

This MSD summarises our best knowledge of the health and safety hazard information of the product and how to safely handle and use the product in the workplace. Each user should read this MSD and consider the information in the context of how the product will be handled and used in the workplace including use in conjunction with other products. If clarification or further information is needed to ensure that an appropriate risk assessment can be made, the user should contact the manufacturer.

PROLONG PRODUCTS ARE MANUFACTURED BY PEERLESS INDUSTRIAL SYSTEMS PTY LTD 79 Robinson Ave, Belmont, Western Australia, 6104

www.peerlessindustrialsystems.com Telephone: (+61) (08) 9477 3788 Facsimile: (+61) (08) 9477 3766

I				